

Prøvningsrapport



Hedevej 8, 7362 Hampen | Sepstrupvej 39A, 8653 Them
Tlf: 40 33 65 75 | CVR 35 48 15 75 | www.asklevstenoggrus.dk

Udtagnings sted:	Sepstrupvej	Udtaget dato:	24-07-2026
Udtaget af:	Esben	Vare:	2-8 mm
Prøvenr:	2026-155	Varenr.:	0
Bemærkning:	0		

EN 933-1

Sigte- størrelse	Gennem- fald %
31,5	100,0
22,4	100,0
16,0	100,0
11,2	100,0
8,0	88,2
5,6	61,6
4,0	40,5
2,8	16,7
2,0	9,5
1,0	1,4
0,50	0,4
0,25	0,2
0,125	0,2
0,063	0,1
Bund:	

DS 405.4

Indhold af lette korn	%
Korn < 2400 kg/M ³	#DIVISION/0!

TI-B 75	
Kritisk absorption af 10 % flint	%
Korn > 2400 kg/m ³	#DIVISION/0!

Densitet / Absorption	pyknometer met.
V.O.T densitet	#DIVISION/0! mg/m ³
Tør densitet	#DIVISION/0! mg/m ³
Tils. densitet	#DIVISION/0! mg/m ³
Absorption	#DIVISION/0! %

U-tal, d60:d10:	0,0
-----------------	-----

Kornkurve

