

Prøvningsrapport



Hedevej 8, 7362 Hampen | Sepstrupvej 39A, 8653 Them
Tlf: 40 33 65 75 | CVR 35 48 15 75 | www.asklevstenoggrus.dk

Udtagnings sted:	Hjøllund	Udtaget dato:	03-08-2026
Udtaget af:	SØO	Vare:	2-8 mm vsk.
Prøvenr:	2026-158	Varenr.:	0
Bemærkning:	0		

EN 933-1

Sigte- størrelse	Gennem- fald %
31,5	100,0
22,4	100,0
16,0	100,0
11,2	100,0
8,0	92,7
5,6	48,5
4,0	16,8
2,8	5,5
2,0	2,8
1,0	1,0
0,50	0,7
0,25	0,5
0,125	0,3
0,063	0,2
Bund:	

DS 405.4

Indhold af lette korn %

Korn < 2400 kg/M ³	#DIVISION/0!
-------------------------------	--------------

TI-B 75

Kritisk absorption af 10 % flint %

Korn > 2400 kg/m ³	#DIVISION/0!
-------------------------------	--------------

Densitet / Absorption pyknometer met.

V.O.T densitet	#DIVISION/0!	mg/m ³
Tør densitet	#DIVISION/0!	mg/m ³
Tils. densitet	#DIVISION/0!	mg/m ³
Absorption	#DIVISION/0!	%

U-tal, d60:d10:	0,0
-----------------	-----

Kornkurve

